

FNM cartridge and capsule filters are constructed with long-proven, absolute rated, Nylon 6,6 membrane. Designed to comply will all FDA requirements for the food industry, these high purity filters are used for removing organisms in nonfermenting liquids and cleaning water. Pore sizes range from 0.10 to 0.65  $\mu m$  and the filter sizes scale from laboratory to full production using identical materials to ensure consistent results.


FNM filters are: optimized for flow and high retention; flushed to reduce extractables; and are 100% integrity tested.

Critical Process provides unrivaled delivery times, technical consulting before purchasing, and very competitively priced high-performance products. Our comprehensive testing & analysis and validation services support your team whenever they need it. Your process experts partnering with our filtration experts is how we deliver your company's solution right the first time.

# Bacteria/Yeast/Mold Removal



CARTRIDGES – Nominal Dimensions Length: 5 to 40 in. (12.7 to 101.6 cm) Outside Diameter: 2.75 in. (7.0 cm)



FNM filters are recommended for:

- Syrups
- Soft Drinks
- Bottled Water
- Container Wash/Rinse Water
- Process Water



CAPSULES – Nominal Dimensions Length: 2 to 30 in. (5.1 to 76.2 cm) Outside Diameter: 3.50 in. (8.9 cm)

## **Maximum Operating Parameters**

	CARTRIDGES	CAPSULES		
Liquid Operational Pressure	N/A	80 psi at 68 °F (5.52 bard at 20 °C)		
Gases Operational Pressure	N/A	60 psi at 68 °F (4.14 bar at 20 °C)		
Operating Temperature (water)	180 °F at 30 psid (82 °C at 2.07 bard) 110 °F at 30 psid (43 °C at 2.07 bard)			
Forward Differential Pressure	80 psid at 68 °F (5.52 bard at 20 °C) (Liquid and Gas)	Liquid - 80 psid at 68 °F (5.52 bard at 20 °C) Gas - 60 psi at 68 °F (4.14 bar at 20 °C)		
Reverse Differential Pressure	50 psid at 68 °F (3.45 bard at 20 °C)	50 psid at 68 °F (3.45 bard at 20 °C)		
Recommended Changeout Pressure	35 psid (2.41 bard)	35 psid (2.41 bard)		

### Sanitization & Sterilization

Filtered Hot Water*	90 °C (194 °F), 30 minutes, multiple cycles, max 3 psid forward flow	N/A		
Inline Steam*	275 °F (135 °C), 30 min, 25+ cycles	N/A		
Autoclave*	250 °F (121 °C), 30 min, 25+ cycles	250 °F (121 °C), 30 min, 25+ cycles		
Chemical Sanitization	Performed using industry standard conce other selected chemicals.	Performed using industry standard concentrations of hydrogen peroxide, peracetic acid, and other selected chemicals.		

<sup>\*</sup>Cartridge Filters – For all elevated temperature procedures above, a stainless-steel support ring is required.

## Filtration Area (Nominal)

	CAPSULES	CARTRIDGES AND CAPSULES			CARTRIDGES	
Length	2"	5"	10"	20"	30"	40"
	5.08cm	12.7cm	25.4cm	50.8cm	76.2cm	101.6cm
Area	1.2 ft <sup>2</sup>	3.3 ft <sup>2</sup>	7.0 ft <sup>2</sup>	14.0 ft <sup>2</sup>	21.0 ft <sup>2</sup>	28.0 ft <sup>2</sup>
	0.11m <sup>2</sup>	0.31m <sup>2</sup>	0.65m <sup>2</sup>	1.30m²	1.95m <sup>2</sup>	2.60m <sup>2</sup>

# **Integrity Testing**

PORE SIZE	DIFFUSION TEST PRESSURE*			E POINT MUM*
μm	PSIG	BARG	PSIG	BARG
0.10	48	3.31	**	**
0.22	35	2.41	50	3.4
0.45	20	1.38	25	1.7
0.65	15	1.03	19	1.3

DIFFUSION SPECIFICATIONS*						
Length	2"	5"	10"	20"	30"	40"
mL/min	≤ 4.3	≤ 12.9	≤ 30	≤ 60	≤ 90	≤ 120

<sup>\*</sup> All specifications are for water wetted membrane

<sup>\*\*</sup> Test pressure exceeds operational limits of capsule filters.
Use the Diffusion Test method.

#### **Construction Materials**

Filtration Media	Nylon 6,6 Membrane with polyester support		
Media Support	Polypropylene		
End Caps, Center Core, Outer Support Cage, Capsule Housing	Polypropylene		
Sealing Method	Thermal Bonding		
O-Rings/Gaskets Cartridges only	Buna, Viton® (or FKM), EPDM, Silicone, FEP Encapsulated Silicone, FEP Encapsulated Viton (or FKM)		

#### Validation

FNM filters are validated using test procedures that comply with ASTM F 838-15(ae1) protocols for the determination of bacterial retention in filters used for liquid filtration. The filters are challenged with the organisms listed below.

0.10μm: Brevundimonas diminuta 0.22μm: Brevundimonas diminuta 0.45μm: Serratia marcescens 0.65μm: Saccharomyces cerevisiae

#### Extractables

FNM filters typically exhibit low levels of non-volatile residues.


### Non-Fiber Releasing

FNM filters comply with Title 21 CFR sections 210.3 (b)(6) and 211.72, for non-fiber releasing filters.

### FDA and EC Compliance


Materials meet the requirements listed by the FDA as appropriate for use in articles intended for repeated food contact as specified in Title 21 CFR sections 174.5, 177.1500, 177.1520, 177.1630, 177.2440, and 177.2600 as applicable. All materials used to make the filters are listed in European Commission Regulation EU/10/2011, Annex 1.

# Flow Rates for FNM Cartridges by Pore Size



Flow rates for Cartridge filters are per 10-inch length. The test fluid is water at ambient temperature.

# Flow Rates for FNM Capsules by Pore Size




Flow rates for Capsule filters are tested using a 2" capsule filter with 1" sanitary inlet and outlet ports. The test fluid is water at ambient temperature. Flow rates for larger capsules will scale with filtration area. Rates will vary based on end configuration of the capsule.


### **FNM Filters Ordering Information**

Fill in the corresponding codes in the boxes below to build your Part Number.

To consult with one of our technical team members, request a quote or place an order: call (603) 880-4420 or contact us here.



\*Additional end configurations available





Nashua, NH 03060 603.880.4420 FAX: 603.880.4536

CriticalProcess.com

The information contained herein is subject to change without notice. The Critical Process Filtration logo is a trademark of Critical Process Filtration, Inc. Viton is a trademark of DuPont Performance Elastomers L.L.C.

© 2025 Critical Process Filtration, Inc. • All Rights Reserved

Data Sheet FNMDS Rev C